

Sika-Trocal® SG 1.5 mm

Polymeric membrane for roof waterproofing

Product Description

Sika-Trocal® SG 1.5 mm is a multi-layer, synthetic roof waterproofing sheet based on premium-quality polyvinyl chloride (PVC) with inlay of glass non-woven according to EN 13956.

Uses

Roof waterproofing membrane for exposed flat roofs:

- Loose laid and mechanically fastened – especially on concave roof structures
- Fully bonded junction areas with contact adhesive Sika-Trocal® C733.
- Roof waterproofing membrane for exposed roof junction zones:
 - Roof waterproofing for junctions and flashings, e.g. wall and parapet junctions, roof lights, etc., which are permanently exposed in installations of Sika-Trocal® SGmA-types roof waterproofing systems with ballast.
 - Roof waterproofing for junctions and flashings in installations of Sika-Trocal® SGK types roof waterproofing systems.

Characteristics / Advantages

- Outstanding resistance to weathering, including permanent UV irradiation
- High resistance to ageing
- High resistance to hailstones
- Resistant to all common environmental influences
- High resistance to mechanical influences
- High tensile strength
- High dimensional stability
- Excellent flexibility in cold temperatures
- High water vapour permeability
- Outstanding weldability
- Recyclable

Approval / Standards

- Polymeric sheets for roof waterproofing according to EN 13956, certified by notified body 1213-CPD-4125/4127 and provided with the CE-mark.
- Reaction to fire according to EN 13501-1.
- External fire performance tested according to ENV 1187 and classified according to EN 13501-5: B_{ROOF}(t1).
- Fire behaviour conforms in accordance with DIN 4102/part 1, class B2.
- Resistant to sparks and radiant heat in accordance with 4102/part 7.
- Official Quality Approvals and Agreement Certificates and approvals.
- Monitoring and assessment by approved laboratories.
- Quality Management system in accordance with EN ISO 9001/14001.
- Production according to responsible Care policy of Chemical Industry.

Roofing



Appearance / Colours	Surface:	slightly structured
	Colours:	
	Top surface:	light grey (nearest RAL 7047) slate grey (nearest RAL 7015)
	Bottom surface:	dark grey
	Top surface of sheet in other colours available on request, subject to minimum order quantities.	
Packaging	Packing unit:	12 rolls per pallet
	Roll length:	15.00 m and 20.00 m
	Roll width:	1.10 m and 2.00 m
Storage Conditions / Shelf-Life	Rolls must be stored in a horizontal position on pallet and protected from direct sunlight, rain and snow. Product does not expire during correct storage.	

Technical Data

Product Declaration	EN 13956	
Visible defects	Pass	EN 1850-2
Length	15.00 / 20.00 m (- 0% / + 5%)	EN 1848-2
Width	1.10 / 2.00 m (- 0.5% / + 1%)	EN 1848-2
Straightness	≤ 30 mm	EN 1848-2
Flatness	≤ 10 mm	EN 1848-2
Effective thickness	1.5 mm (- 5% / + 10%)	EN 1849-2
Mass per unit area	1.9 kg/m ² (- 5% / + 10%)	EN 1849-2
Water tightness	Pass	EN 1928
Effects of liquid chemicals, including water	On request	EN 1847
External fire performance Part 1-4	B _{ROOF} (t1) <20°	EN 13501-5
Reaction to fire	Class E	EN ISO 11925-2, classification to EN 13501-1
Hail resistance		EN 13583
rigid substrate	≥ 20 m/s	
flexible substrate	≥ 30 m/s	
Joint peel resistance	≥ 300 N/50 mm	EN 12316-2
Joint shear resistance	≥ 500 N/50 mm	EN 12317-2
Water vapour transmission properties	μ = 20'000	EN 1931
Tensile stress		EN 12311-2
longitudinal (md)¹⁾	≥ 9.5 N/mm ²	
transversal (cmd)²⁾	≥ 8.5 N/mm ²	
Elongation		EN 12311-2
longitudinal (md)¹⁾	≥ 200 %	
transversal (cmd)²⁾	≥ 200 %	
Resistance to impact		EN 12691
hard substrate	≥ 600 mm	
soft substrate	≥ 900 mm	
Tear strength		EN 12310-2
longitudinal (md)¹⁾	≥ 100 N	
transversal (cmd)²⁾	≥ 100 N	
Dimension stability		EN 1107-2
longitudinal (md)¹⁾	≤ 0.3 %	
transversal (cmd)²⁾	≤ 0.3 %	
Foldability at low temperature	≤ -25 °C	EN 495-5
UV exposure	Pass (> 5'000 h)	EN 1297

¹⁾ md = machine direction

²⁾ cmd = cross machine direction

System Information

System Structure

Ancillary products according to local price list:

- Sika-Trocal® S, 1.5mm unreinforced sheet for detailing
 - Moulded corner pieces, prefabricated corners and pipe flashings
 - Sika-Trocal® Metal Sheet Type S
 - Sika-Trocal® Cleaner L 100
 - Sika-Trocal® Welding Agent
 - Sika-Trocal® Seam Sealant
 - Sika-Trocal® C 733 (Contact adhesive)
-

Application Details

Substrate Quality

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc.

Sika-Trocal® SG, 1.5 mm must be separated from any incompatible substrates by an effective separation layer to prevent accelerated ageing. Prevent direct contact with bitumen, tar, fat, oil, solvent containing materials and other plastic materials, e.g. expanded polystyrene (EPS), extruded polystyrene (XPS), polyurethane (PUR), polyisocyanurate (PIR) or phenolic foam (PF) as this could adversely affect the product properties.

Application Conditions / Limits

Temperature

The use of Sika-Trocal® SG, 1.5 mm membranes is limited to geographical locations with average monthly minimum temperatures of -25 °C. Permanent ambient temperature during use is limited to +50 °C.

Compatibility

Not compatible with direct contact to other plastics, e.g. EPS, XPS, PUR, PIR, PF. Not resistant to tar, bitumen, oil and solvent containing materials.

Installation Instructions

Installation Method / Tools

Installation procedure:

According to the valid installation instructions of manufacturer for Sika-Trocal® S-types for mechanical fastened system, for Sika-Trocal® SGmA-types for ballasted system and Sika-Trocal® SGK-types for adhered system.

Fixing Method:

Loosely laid and mechanically fastened.

The roof waterproofing membrane is installed by loose laying and mechanical fastening in seam overlaps or independent from overlaps.

Fully adhered junction area.

The roof waterproofing membrane is bonded to substrate by contact adhesive Sika-Trocal® C733. Seam overlaps are welded by hot air or cold welding.

Welding Method:

Overlap seams are welded by electric hot welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with controlled hot air temperature capability.

Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic situation prior to welding. The effective width of welded overlaps should be minimum 20 mm.

If local weather conditions allow cold welding of sheet overlaps with Sika-Trocal® Welding Agent, it is permitted for Sika-Trocal® SG 1.5 mm with mechanically fastened system in overlap or independent from seam. The effective width of welded overlap by cold welding should be minimum 30 mm.

The seams must be mechanically tested with screw driver or steel needle to ensure the integrity/completion of the weld. Any imperfections must be rectified by hot air welding.

Edges must be sealed by Sika-Trocal® liquid PVC.

Notes on Installation / Limits

Installation works must be carried out only by Sika instructed contractors for roofing.

Temperature limits for the installation of the membrane:

Substrate temperature: -25 °C min. / +60 °C max. for hot air welding
 +5 °C min. / +60 °C max. for cold welding

Ambient temperature: -15 °C min. / +60 °C max. for hot air welding
 +5 °C min. / +60 °C max. for cold welding

Installation of some ancillary products, e.g. contact adhesives/thinners is limited to temperatures above +5 °C. Please refer to the respective Product Data Sheets.

Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.
Ecology, Health and Safety Information	The product does not fall within the EC-regulation of hazardous goods. As a result, a material safety data sheet following EC-Guideline 91/155 EWG is not needed to bring the product to the market, transport or use it. The product does not damage the environment when used as specified.
Protective Measures	Fresh air ventilation must be ensured, when working (welding) in closed rooms. Local safety regulations must be observed.
Transportation Class	The product is not classified as hazardous good for transport.
Disposal	The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.
Legal Note	The information, and, in particular, the recommendations relating to the application and end- use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



SIKA LIMITED
 Head Office · Watchmead · Welwyn Garden City
 Hertfordshire · AL7 1BQ · United Kingdom
 Phone: +44 1 707 394444 · Fax: +44 1 707 329129
 www.sika.co.uk

Sika-Trocal®